

ELASTOSIL® 4000

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1

Sealants, Elastic, Construction

General Information			
Uncured Properties	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183
Extrusion Rate (23.0°C)	450	ml/min	
Consistency	non-sag		ISO 7390
Skin Forming Time ¹ (23°C)	20.0	min	
Cured Properties	Nominal Value	Unit	Test Method
Tensile Modulus (100% Secant)	0.350	MPa	ISO 8339
Tensile Strength	0.600	MPa	ISO 8339
Tear Strength	4.20	kN/m	ISO 34
NOTE			
1.	50% R.H		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

