

LNP™ THERMOTUF™ VX99809 compound

Polyamide

SABIC Innovative Plastics

Message:

LNP THERMOTUF VX99809 is a compound based on Super Tough Nylon resin containing Proprietary Filler(s). Added faeture of this material is: High Impact.

Also known as: LNP* THERMOTUF* Compound PDX-V-99809

Product reorder name: VX99809

General Information			
Filler / Reinforcement	Proprietary		
Features	High Impact Resistance		
	Ultra High Toughness		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow : 24 hr	2.0 to 3.0	%	
Across Flow : 24 hr	2.0 to 3.0	%	
Water Absorption			
24 hr, 50% RH	0.92	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.9	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1980	MPa	ASTM D638
--	1880	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	43.3	MPa	ASTM D638
Yield	42.2	MPa	ISO 527-2/5
Break ³	40.7	MPa	ASTM D638
Break	41.5	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	3.9	%	ASTM D638
Yield	3.7	%	ISO 527-2/5
Break ⁵	75	%	ASTM D638
Break	130	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	1220	MPa	ASTM D790
-- ⁷	1300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	890	J/m	ASTM D256
23°C ⁸	83	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1300	J/m	ASTM D4812
23°C ⁹	150	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy	49.9	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	178	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁰	100	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	49.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	48.0	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	260 to 271	°C	
Middle Temperature	277 to 288	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	282 to 293	°C	
Mold Temperature	93.3 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	80*10*4		
9.	80*10*4		
10.	80*10*4 mm		
11.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

