

SD POLYCA™ LD2050-AAH14

Polycarbonate

Sumika Styron Polycarbonate Limited

Message:

SD POLYCA LD2050 series are light diffusion polycarbonate resins for LCD TV and LED lighting and lamp cover shade.

General Information			
UL YellowCard	E123529-100590580		
Uses	LCD application		
	LEDs		
Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	6.00 - 22.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	60.0	MPa	ISO 527-2
Tensile Strain (Break)	100	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	20	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	126	°C	ISO 75-2/A
Optical	Nominal Value	Unit	Test Method
Transmittance			ASTM D1003
1000 µm	88.0	%	ASTM D1003
1600 µm	85.0	%	ASTM D1003
2000 µm	81.0	%	ASTM D1003
3000 µm	72.0	%	ASTM D1003
Haze			ASTM D1003
1000 µm	96	%	ASTM D1003
1600 µm	98	%	ASTM D1003
2000 µm	99	%	ASTM D1003
3000 µm	99	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Light Diffusion			Internal method
1.00 mm	23.0	°	Internal method
1.60 mm	24.0	°	Internal method
2.00 mm	32.0	°	Internal method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

