

Luranyl® KR 2454/3 G2

Polyphenylene Ether + PS

ROMIRA GmbH

Message:

PPE+PS-I Blend with 10% glass fibre; halogen free flame retardant; high heat resistance

General Information	
UL YellowCard	E148878-223648
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight
Additive	Flame retardancy
Features	Heat resistance, high
	Halogen-free
	Flame retardancy
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/21.6 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage (23°C, 3.20 mm)	0.30 - 0.50	%	ISO 294-4
Water Absorption (23°C, 24 hr)	< 0.10	%	ISO 62

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4500	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	75.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2/5
Flexural Stress ¹ (23°C)	140	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	10	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	35	kJ/m ²	ISO 179/1eU
23°C	35	kJ/m ²	ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	133	°C	ISO 75-2/A
Vicat Softening Temperature	138	°C	ISO 306/B50
CLTE - Flow (23 to 80°C)	4.0E-6 - 5.0E-6	cm/cm/°C	ISO 11359-2

Thermal Conductivity	0.21	W/m/K	DIN 52612
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-1		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.050	%	
Processing (Melt) Temp	260 - 290	°C	
Mold Temperature	60.0 - 100	°C	
Injection Rate	Moderate		
Screw Speed	12 - 18	rpm	
Injection instructions			
Maximum Residence Time: 4 to 10 minInjection Pressure: moderate to high			
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.050	%	
Cylinder Zone 1 Temp.	240 - 270	°C	
Cylinder Zone 2 Temp.	240 - 270	°C	
Cylinder Zone 3 Temp.	240 - 270	°C	
Cylinder Zone 4 Temp.	240 - 270	°C	
Cylinder Zone 5 Temp.	240 - 270	°C	
Melt Temperature	< 270	°C	
Extrusion instructions			
Maximum Residence Time: 4 ot 10 min			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT