

Durethan® BKV 50 H2.0 901510

Polyamide 6

LANXESS GmbH

Message:

PA 6, 50 % glass fibers, injection molding, heat-aging stabilized

General Information				
UL YellowCard	E245249-473600			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight			
Additive	heat stabilizer			
Features	Thermal Stability			
Agency Ratings	EC 1907/2006 (REACH)			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.57	--	g/cm ³	ASTM D792
23°C	1.57	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 3.00mm ¹	0.85	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 3.00mm ²	0.050	--	%	ISO 2577
Flow direction: 280°C, 3.00mm ³	0.16	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 3.00mm ⁴	0.020	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	5.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.5	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	250	109	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	15000	9500	MPa	ASTM D638
23°C	16300	9800	MPa	ISO 527-2/1
Tensile Strength				
Fracture, 23°C	210	150	MPa	ASTM D638
Fracture, 23°C	220	140	MPa	ISO 527-2/5
Tensile Elongation				
Fracture, 23°C	2.0	4.0	%	ASTM D638

Fracture, 23°C	3.0	5.0	%	ISO 527-2/5
Tensile Creep Modulus				ISO 899-1
1 hr	--	8100	MPa	ISO 899-1
1000 hr	--	6600	MPa	ISO 899-1
Flexural Modulus				
23°C	13500	7690	MPa	ASTM D790
23°C ⁶	15100	9700	MPa	ISO 178/A
Flexural Strength				
23°C	350	220	MPa	ASTM D790
23°C ⁷	360	230	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁸ (23°C)	3.0	5.0	%	ISO 178/A
Burning Behavior ⁹ (> 1.00 mm)	passed	--		ISO 3795
ISO Shortname	PA 6, GHR, 14-160, GF50	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	15	13	kJ/m ²	ISO 179/1eA
23°C	20	25	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	85	80	kJ/m ²	ISO 179/1eU
23°C	100	100	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
-40°C, 3.18 mm	130	130	J/m	ASTM D256
23°C, 3.18 mm	170	200	J/m	ASTM D256
-30°C	12	12	kJ/m ²	ISO 180/1A
23°C	20	25	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	80	80	kJ/m ²	ISO 180/1U
23°C	85	85	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	3.70	--	J	ISO 6603-2
23°C	4.20	8.90	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	1060	--	N	ISO 6603-2
23°C	1200	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				

0.45 MPa, unannealed, 39.9mm	215	--	°C	ASTM D648
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed	205	--	°C	ISO 75-2/A
1.8 MPa, annealing, 3.99mm	200	--	°C	ASTM D648
Vicat Softening Temperature	> 200	--	°C	ISO 306/B50, ISO 306/B120
Melting Temperature ¹⁰	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	7.0E-5	--	cm/cm/°C	ISO 11359-2
RTI Elec				UL 746
0.750 mm	65.0	--	°C	UL 746
1.50 mm	120	--	°C	UL 746
RTI Imp				UL 746
0.750 mm	65.0	--	°C	UL 746
1.50 mm	95.0	--	°C	UL 746
RTI				UL 746
0.750 mm	65.0	--	°C	UL 746
1.50 mm	140	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13 - 1.0E+14	1.0E+12 - 1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15 - 1.0E+16	1.0E+12 - 1.0E+13	ohms·cm	IEC 60093
Dielectric Strength				IEC 60243-1
23°C, 1.00 mm	35	26	kV/mm	IEC 60243-1
23°C, 3.00 mm	40	35	kV/mm	IEC 60243-1
Dielectric Constant				IEC 60250
23°C, 50 Hz ¹¹	4.00	--		IEC 60250
23°C, 1 MHz ¹²	4.00	5.00		IEC 60250
23°C, 100 Hz	5.30	14.2		IEC 60250
23°C, 1 MHz	4.30	5.00		IEC 60250
Dissipation Factor				IEC 60250
23°C, 50 Hz	0.010	--		IEC 60250
23°C, 100 Hz	0.036	0.32		IEC 60250
	0.015	0.14		
23°C, 1 MHz	0.024	0.089		IEC 60250
Comparative Tracking Index				
Solution a	550	--	V	IEC 60112
--	--	375	V	ASTM D3638
Flammability	Dry	Conditioned	Unit	Test Method

Flame Rating				UL 94
0.750 mm	HB	--		UL 94
1.50 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94
3.00 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index ¹³	24	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	270 - 290		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				

1.	150x105x3mm, 80°C MT, 400 bar
2.	150x105x3mm
3.	150x105x3mm, 80°C MT, 400 bar
4.	150x105x3mm
5.	1.0 mm/min
6.	2.0 mm/min
7.	2.0 mm/min
8.	2 mm/min
9.	US-FMVSS302
10.	10°C/min
11.	Tinfoil Electrodes
12.	Tinfoil Electrodes
13.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT