

BIPEX B0620FN17

Polybutylene Terephthalate

Ginar Technology Co., LTD.

Message:

BIPEX B0620FN17 is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
UL YellowCard	E154352-223874		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogenated		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.00 mm)	0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	138	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	7930	MPa	ASTM D790A
Flexural Strength	221	MPa	ASTM D790A

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	215	°C	ASTM D648
Peak Melting Temperature	220	°C	ASTM D789

Flammability	Nominal Value	Test Method
Flame Rating		UL 94
1.59 mm	V-0	
3.18 mm	V-0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

