

UBE Nylon 1015GC6

Polyamide 6

UBE Engineering Plastics, S.A.

Message:

UBE Nylon 1015GC6 is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

- Flame Rated
- Chemical Resistant
- Heat Resistant
- High Strength
- Impact Resistant

General Information				
UL YellowCard		E173981-238518	E48133-240231	
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		Good Abrasion Resistance		
		Good Chemical Resistance		
		Good Impact Resistance		
		High Heat Resistance		
		High Rigidity		
		High Strength		
		Oil Resistant		
		Self Lubricating		
		Solvent Resistant		
		Sound Damping		
Vibration Damping				
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.36	--	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.70	--	%	ASTM D955
Water Absorption (Saturation)	6.6	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
M-Scale	100	--		
R-Scale	120	110		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Yield)	167	98.0	MPa	ASTM D638
Tensile Elongation (Yield)	5.0	6.0	%	ASTM D638
Flexural Modulus	7840	4410	MPa	ASTM D790

Flexural Strength (Yield)	245	127	MPa	ASTM D790
Compressive Strength	27.4	15.7	MPa	ASTM D695
Shear Strength	85.2	58.8	MPa	ASTM D732
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
-30°C	78	140	J/m	
23°C	110	230	J/m	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	215	--	°C	ASTM D648
Melting Temperature	215 to 225	--	°C	
CLTE - Flow	2.5E-5	--	cm/cm/°C	ASTM D696
RTI Elec (0.794 mm)	65.0	--	°C	UL 746
RTI Imp (0.794 mm)	65.0	--	°C	UL 746
RTI Str (0.794 mm)	65.0	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	ASTM D257
Dielectric Constant				ASTM D150
60 Hz	4.20	--		
1 MHz	3.80	--		
Dissipation Factor				ASTM D150
60 Hz	0.010	--		
1 MHz	0.020	--		
Arc Resistance (0.794 mm)	121	--	sec	ASTM D495
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.794 mm)	HB	--		UL 94
Injection	Dry	Unit		
Suggested Max Moisture	0.10		%	
Rear Temperature	240		°C	
Middle Temperature	265		°C	
Front Temperature	275		°C	
Nozzle Temperature	275		°C	
Processing (Melt) Temp	285		°C	
Mold Temperature	70.0 to 80.0		°C	
Injection Pressure	83.2		MPa	
Back Pressure	9.80		MPa	
Screw Speed	100 to 130		rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

