

# Sanren Q200 (1st-grade)

Low Density Polyethylene

SINOPEC Shanghai Petrochemical Co. Ltd.

## Message:

The oblate pellet product is colourless with excellent chemical stability. Under the normal conditions, the product is acid resistant, alkali resistant, and salt resistant. It possesses certain mechanical properties. good dielectric characteristics and excellent light transmittance.

Scope of Application: Light-duty film, Laminated film and small size injection mouldings.

General Information	
Features	High Light Transmission
	Low density
	Homopolymer
	Good electrical performance
	alkali resistance
	acid resistance
Uses	Films
	Laminate
Appearance	Colorless
Forms	Particle
Processing Method	Blow molding
	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm <sup>3</sup>	Internal method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.6 - 2.4	g/10 min	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	> 11.0	MPa	Internal method
Tensile Elongation (Break)	> 550	%	Internal method
Optical	Nominal Value	Unit	Test Method
Haze	< 10	%	Internal method
Additional Information	Nominal Value	Unit	
Blocking	0.0260	MPa	
Fish Eye			
	0.300 to 2.00mm	pcs/1200 cm <sup>2</sup>	
	Linking: 0.500 to 2.00mm	pcs/20 cm <sup>2</sup>	
Hue			
Impurities (> 100.0 μm)		pcs/100 g	

Cleanliness: <15 pieces/kg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

