

DOWLEX™ NG 2038.11B

Polyethylene Resin
The Dow Chemical Company

Message:

DOWLEX™ NG 2038.11B is a Polyethylene Resin material. It is available in Latin America.
Important attributes of DOWLEX™ NG 2038.11B are:
Antiblock
Processing Aid
Slip
Typical application of DOWLEX™ NG 2038.11B: Food Contact Applications

General Information			
Additive	Antiblock (1250 ppm)		
	Slip (500 ppm)		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.2a		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.936	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	µm	Internal Method
Film Puncture Resistance (38 µm)	8.00	J/cm ³	
Secant Modulus			ASTM D882
2% Secant, MD : 38 µm	370	MPa	ASTM D882
2% Secant, TD : 38 µm	425	MPa	
Tensile Strength			
MD : Yield,38 µm	17.0	MPa	
TD : Yield,38 µm	19.0	MPa	ASTM D882
MD : Break, 38 µm	46.0	MPa	
TD : Break, 38 µm	41.0	MPa	
Tensile Elongation			
MD : Break, 38 µm	900	%	ASTM D882
TD : Break, 38 µm	1100	%	
Dart Drop Impact (38 µm)	180	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 38 µm	80	g	ASTM D1922
TD : 38 µm	840	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 37.5 µm)	60		ASTM D2457
Haze (37.5 µm)	12	%	ASTM D1003

Extrusion	Nominal Value	Unit
Melt Temperature	233	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

