

Kumho ABS 728W

Acrylonitrile Butadiene Styrene
Korea Kumho Petrochemical Co., Ltd.

Message:

Features: High gloss, weather stable
Applications: Prosucts demanding for gloss: Sweeper, Wasshing machine cover etc

General Information			
Features	Good Weather Resistance		
	High Gloss		
Uses	Washer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
200°C/21.6 kg	60	g/10 min	ASTM D1238
220°C/10.0 kg	40	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	0.50 to 0.80	%	ASTM D955
--	0.50 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	46.1	MPa	ASTM D638
Yield	44.0	MPa	ISO 527-2
Tensile Elongation			
Yield	20	%	ASTM D638
Break	20	%	ISO 527-2
Flexural Modulus			
--	2160	MPa	ASTM D790
--	23000	MPa	ISO 178
Flexural Stress			
--	66.0	MPa	ISO 178
Yield	63.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	22	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.20 mm	250	J/m	ASTM D256
23°C, 6.40 mm	200	J/m	ASTM D256

23°C	21	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	89.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	86.0	°C	ASTM D648
1.8 MPa, Unannealed	78.0	°C	ISO 75-2/A
Vicat Softening Temperature	96.0	°C	ISO 306/B50, ASTM D1525 1
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT