

Bapolene® 80

Polyethylene Terephthalate

Bamberger Polymers, Inc.

Message:

Copolymer resin with a slow rate of crystallization and superior optical properties.

General Information	
Features	Copolymer Opticals
Uses	Blow Molding Applications Containers Food Containers Household Goods
Processing Method	Blow Molding Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ASTM D1505
Acetaldehyde	< 2.0	ppm	
Crystallinity	> 50	%	
Moisture Content	0.10	%	
Viscosity	0.770 to 0.810		
Diethylene Glycol	< 2.3	wt%	
Thermal	Nominal Value	Unit	
Melting Temperature	247	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT