Texalan® 7 Series 772D

Thermoplastic Polyurethane Elastomer Alloy

Austin Novel Materials Co. Ltd.

Message:

Texalan® 7 Series 772D is a Thermoplastic Polyurethane Elastomer Alloy (TPU Alloy) material. It is available in Asia Pacific, Europe, or North America for blow molding, calendering, coextrusion, extrusion, film extrusion, or injection molding.

Important attributes of Texalan® 7 Series 772D are:

Chemical Resistant

High Strength

Impact Resistant

Low Temperature Resistant

Wear Resistant

General Information								
Features	Good Abrasion Resistance							
	High Elasticity High Impact Resistance High Tensile Strength Low Temperature Resistant							
						Oil Resistant		
					Processing Method	Blow Molding		
Calendering								
Coextrusion								
Extrusion								
Film Extrusion								
Injection Molding								
Physical	Nominal Value	Unit	Test Method					
Density	1.20 to 1.24	g/cm³	ISO 1183					
Hardness	Nominal Value	Unit	Test Method					

Physical	Nominal Value	Unit	Test Method
Density	1.20 to 1.24	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	69 to 75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Abrasion Resistance	< 35.0	mm³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	22.0	MPa	
300% Strain	> 32.0	MPa	
Tensile Stress (Yield)	> 52.0	MPa	ISO 37
Tensile Elongation (Break)	> 350	%	ISO 37
Tear Strength	> 110	kN/m	ISO 34-1
Compression Set (70°C)	< 32	%	ISO 815

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

