

ELASTOSIL® LR 3153 A/B

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, LSR

Tents, Technical Textiles

Coating of Fabrics and Textiles, Technical Textiles

Technical Textiles, Technical Textiles

Architectural Textiles, Technical Textiles

Bonding for HTV, Plastics and Rubber Processing

Electrically Conductive Rollers, Plastics and Rubber Processing

Electrically Conductive Rollers, Printing Industry

General Information			
Uses	Fabric Coatings		
	Non-wovens Coatings		
	Textile Applications		
	Wovens Coatings		
Processing Method	Coating		
	Injection Molding		
	Liquid Injection Molding (LIM)		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.07	g/cm ³	ISO 1183
Viscosity	140	Pa · s	Brookfield
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	60		DIN 53505
Tensile Strength	7.40	MPa	DIN 53504
Tensile Elongation at Break	170	%	DIN 53504
Tear Strength	14.0	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT