

ULTEM™ 9090 resin

Polyether Imide

SABIC Innovative Plastics

Message:

Polyetherimide Blend with improved Ductility and Detergent resistance. Meets FAR 25.853 and OSU 55/55 heat release and provides low toxicity, smoke and flame evolution.

General Information			
Features	Ductile		
	Low Smoke Emission		
	Low Toxicity		
Agency Ratings	FAR 25.853		
	OSU 55/55		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	10	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (360°C/5.0 kg)	14.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2900	MPa	ASTM D638
Tensile Strength			
Yield ²	95.0	MPa	ASTM D638
Yield	97.0	MPa	ISO 527-2/50
Break ³	90.0	MPa	ASTM D638
Break	80.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	7.0	%	ISO 527-2/50
Break ⁵	85	%	ASTM D638
Break	80	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	3000	MPa	ASTM D790
-- ⁷	2800	MPa	ISO 178
Flexural Stress			
--	136	MPa	ISO 178
Yield, 50.0 mm Span ⁸	140	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	11	kJ/m ²	ISO 179/2C
Notched Izod Impact			
23°C	70	J/m	ASTM D256
-30°C ⁹	6.0	kJ/m ²	ISO 180/1A
23°C ¹⁰	6.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹¹			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Reverse Notch Izod Impact (3.20 mm)	3300	J/m	ASTM D256
Instrumented Dart Impact			ASTM D3763
-20°C, Total Energy	88.0	J	
0°C, Total Energy	99.0	J	
23°C, Total Energy	88.0	J	
Instrumented Impact, Ductility			ASTM D3763
-20°C	90	%	
0°C	100	%	
23°C	100	%	
NBS Smoke Density - Flaming, Ds, 4 min	0.700		ASTM E662
OSU Peak Heat Release Rate ¹²	45.0	kW/m ²	FAR 25.853
OSU Total Heat Release ¹³	15.0	kW · min/m ²	FAR 25.853
Vertical Burn Test - Test a (60 s), passes at	1.0	sec	FAR 25.853
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 6.40 mm	214	°C	ASTM D648
0.45 MPa, Unannealed, 100 mm Span ¹⁴	205	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 6.40 mm	204	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹⁵	190	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	219	°C	ISO 306/A50
--	212	°C	ISO 306/B50, ISO 306/B120
CLTE			
Flow : -20 to 150°C	5.6E-5	cm/cm/°C	ASTM E831
Flow : 23 to 150°C	5.0E-5	cm/cm/°C	ISO 11359-2
Transverse : -20 to 150°C	5.5E-5	cm/cm/°C	ASTM E831
Transverse : 23 to 150°C	5.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.19	W/m/K	ASTM C177
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	46	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	6.0 to 8.0	hr	
Drying Time, Maximum	24	hr	

Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	330 to 390	°C
Middle Temperature	335 to 390	°C
Front Temperature	345 to 390	°C
Nozzle Temperature	345 to 390	°C
Processing (Melt) Temp	355 to 390	°C
Mold Temperature	130 to 160	°C
Back Pressure	0.300 to 0.700	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.025 to 0.076	mm

NOTE

1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4
10.	80*10*4
11.	80*10*4
12.	5 minute test
13.	2 minute test
14.	120*10*4 mm
15.	120*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

