

PIVINEL™ 116-80H-LF

Polyvinyl Chloride

HELLENIC CABLES S.A.

Message:

Description: PVC based compound for inner sheaths (filler) for energy cables

Specifications: PVC bending (BS-5467), CL9

Packaging: In PE bags of 25 kg or in big bags of approximately 1000 kg

Types of cables where it can be used: XLPE/PVC/SWA/PVC, XLPE/PVC/AWA/PVC

General Information		
Uses	Wire & Cable Applications	
RoHS Compliance	RoHS Compliant	
Processing Method	Extrusion	
Physical	Nominal Value	Unit
Specific Gravity	1.66	g/cm ³
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	145	°C
Cylinder Zone 2 Temp.	155	°C
Cylinder Zone 3 Temp.	160	°C
Cylinder Zone 4 Temp.	165	°C
Cylinder Zone 5 Temp.	170	°C
Cylinder Zone 6 Temp.	170	°C
Cylinder Zone 7 Temp.	170	°C
Head Temperature	170	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

