

HiFill® PA6/6 IM 408 HS L

Polyamide 66
Techmer Engineered Solutions

Message:

HiFill® PA6/6 IM 408 HS L is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in North America.

Characteristics include:

Heat Stabilizer
Impact Modified
Impact Resistant
Lubricated

General Information			
Additive	Heat Stabilizer		
	Impact Modifier		
	Lubricant		
Features	Heat Stabilized		
	High Impact Resistance		
	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.5	%	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	59.3	MPa	ASTM D638
Tensile Elongation (Yield)	80	%	ASTM D638
Flexural Modulus	1900	MPa	ASTM D790
Flexural Strength	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C, 3.18 mm	53	J/m	
23°C, 3.18 mm	210	J/m	
Unnotched Izod Impact (3.18 mm)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	224	°C	

1.8 MPa, Unannealed	71.1	°C	
CLTE - Flow	7.9E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength ¹	17	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	2.0 to 4.0	%	
Rear Temperature	266 to 304	°C	
Middle Temperature	266 to 304	°C	
Front Temperature	266 to 304	°C	
Processing (Melt) Temp	260 to 282	°C	
Mold Temperature	65.6 to 93.3	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

