

Zytel® 73G15HSL BK363

NYLON RESIN
DuPont Performance Polymers

Message:
15% Glass Reinforced, Heat Stabilized, Polyamide 6

General Information				
UL YellowCard		E41938-234330		
Filler / Reinforcement		Glass Fiber, 15% Filler by Weight		
Additive		Heat Stabilizer		
		Lubricant		
		Mold Release		
Features		Heat Stabilized		
		Lubricated		
Forms		Pellets		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA6-GF15<		
Resin ID (ISO 1043)		PA6-GF15		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.25	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.80	--	%	
Flow	0.30	--	%	
Water Absorption				ISO 62
23°C, 24 hr, 2.00 mm	7.6	--	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	2.5	--	%	
Viscosity Number	150	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	6500	4000	MPa	ISO 527-2
Tensile Stress (Break)	130	80.0	MPa	ISO 527-2
Tensile Strain (Break)	2.3	10	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	7.0	kJ/m ²	
23°C	6.0	7.0	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU

-30°C	40	40	kJ/m ²	
23°C	40	70	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	204	--	°C	ISO 75-2/A
Vicat Softening Temperature	215	--	°C	ISO 306/B50
Melting Temperature ¹	221	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	3.5E-5	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength	22	--	kV/mm	IEC 60243-1
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (1.00 mm)	25	--	mm/min	ISO 3795
Flammability Classification (1.50 mm)	HB	--		IEC 60695-11-10, -20
Oxygen Index	21	--	%	ISO 4589-2
Fill Analysis	Dry	Conditioned	Unit	Test Method
Thermal Conductivity of Melt	0.20	--	W/m/K	
Emission of Organic Compounds	8.50	--	µgC/g	VDA 277
Odor	4	--		VDA 270
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT