

Celstran® PP-GF50-02-Black

Polypropylene
Celanese Corporation

Message:
50% long strand glass fiber chemically coupled polypropylene, Black

General Information			
UL YellowCard	E113269-237806		
Filler / Reinforcement	Long glass fiber, 50% filler by weight		
Features	Chemical coupling		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792, ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	11000	MPa	ASTM D638
--	10600	MPa	ISO 527-2/1A/1
Tensile Strength			
Fracture, 23°C	121	MPa	ASTM D638
Fracture	130	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	1.4	%	ASTM D638
Fracture	1.8	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	10800	MPa	ISO 178
Flexural Stress (23°C)	230	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	34	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	154	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	220 - 230	°C	
Middle Temperature	220 - 230	°C	
Front Temperature	230 - 250	°C	
Nozzle Temperature	230 - 250	°C	
Processing (Melt) Temp	230 - 250	°C	

Mold Temperature	40.0 - 70.0	°C
------------------	-------------	----

Injection instructions

Zone 4 Temperature: 230 to 250°C Feed Temperature: 20 to 50°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT