

Durethan® BKV 215 W1 902176

Polyamide 6

LANXESS GmbH

Message:

PA 6-Copolymer, 15 % glass fibers, injection molding, improved impact strength, weather stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 15% filler by weight		
Features		Impact resistance, good		
		Good weather resistance		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.18	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.60	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.10	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.50	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.10	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	4400	2100	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	85.0	50.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.7	20	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	3900	1900	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	115	50.0	MPa	ISO 178/A
23°C ⁶	135	65.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.5	7.5	%	ISO 178/A
Burning Behavior ⁸	passed	--		ISO 3795
ISO Shortname	PA 6/66-HI, GLR, 14-040, GF15 --			ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	80	80	kJ/m ²	ISO 179/1eU
23°C	65	100	kJ/m ²	ISO 179/1eU

Notched Izod Impact (23°C)	20	30	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	60	60	kJ/m ²	ISO 180/1U
23°C	55	80	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	3.10	--	J	ISO 6603-2
23°C	7.30	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	785	--	N	ISO 6603-2
23°C	1760	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	205	--	°C	ISO 75-2/B
1.8 MPa, not annealed	180	--	°C	ISO 75-2/A
8.0 MPa, not annealed	60.0	--	°C	ISO 75-2/C
Vicat Softening Temperature	193	--	°C	ISO 306/B120
Melting Temperature ⁹	214	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	5.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.6E-4	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 290		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			

8.	US-FMVSS302
9.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

