

Hyosung Polyketone M630A

Polyketone, Aliphatic

Hyosung Corporation

Message:

Hyosung Polyketone M630A
High viscosity grade for injection molding & extrusion (Natural color)

General Information			
Features	High Viscosity		
Appearance	Natural Color		
Processing Method	Extrusion		
	Injection Molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (240°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.8 to 2.0	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.50	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	107		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	60.8	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	> 300	%	ASTM D638
Flexural Modulus (23°C)	1570	MPa	ASTM D790
Flexural Strength (23°C)	60.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	177	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	210	°C	
1.8 MPa, Unannealed	105	°C	
Melting Temperature	220	°C	ASTM D1525
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

