

# Kanghui KH2085

Polybutylene Terephthalate

Yingkou Kanghui Petrochemical Co., LTD.

## Message:

PBT is made from PTA and BD which form into polybutylene terephthalate (referred as PBT) after the continuous process of esterification and polycondensation. It is a kind of crystalline and thermoplastic polyester with the features of high heat resistance, toughness, fatigue resistance, high insulation resistance, dimensional stability, preferable elasticity and dyeing property and used in the field of automotive, electronic and electrical appliances, industrial machinery, civil and industrial textile, polymer alloy and blending industry, etc..

## General Information

Features	Good dimensional stability Fatigue resistance Heat resistance, high Good toughness
Uses	Electrical/Electronic Applications Electrical appliances Industrial application Mixing Application in Automobile Field

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30 - 1.32	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	50 - 55	g/10 min	ASTM D1238
Color b	1.00 - 3.00		Q/KHS001
Color L	> 95.0		Q/KHS001
Particle Mass	1.90 - 2.10	g/100 pcs	Q/KHS001
Intrinsic Viscosity	0.84 - 0.86	dl/g	Q/KHS001
Moisture Content		wt%	Q/KHS001
Ash Content		mg/kg	Q/KHS001
Carboxyl End Groups		mol/t	Q/KHS001
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	50.0 - 60.0	MPa	ASTM D638
Tensile Elongation (Break)	> 50	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	> 39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	> 222	°C	Q/KHS001
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (2.00 mm)	> 20	kV/mm	ASTM D149

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

