

DENIFORM 3010

Acetal (POM) Copolymer

Vamp Tech

Message:

POM, 30% glass fiber reinforced, not Flame Retardant compound, very good mechanical properties.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm ³	ASTM D792
Water Absorption (Saturation)	0.80	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ASTM D638
Tensile Strength (Yield)	120	MPa	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	4.5	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	160	°C	ASTM D648A
Vicat Softening Temperature	160	°C	ASTM D1525 ¹
RTI Elec	90.0	°C	UL 746
RTI Imp	90.0	°C	UL 746
RTI Str	90.0	°C	UL 746
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	190	°C	
Mold Temperature	90.0	°C	
NOTE			
1.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

