

Lucent TPO TPO-20T

Polyolefin

Lucent Polymers, Inc.

Message:

20% Mineral Filled Thermoplastic Polyolefin

Melt Flow Adjustable for Application

Colors Available

Add "U" for UV Stabilized

Add "H" for Heat Stabilized

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Appearance	Colors Available		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	21.4	MPa	ASTM D638
Tensile Elongation (Break)	> 25	%	ASTM D638
Flexural Modulus	862	MPa	ASTM D790
Flexural Strength	30.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	43.3	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT