

HiFill FR® PC GF10 FR BK

Polycarbonate

Techmer Engineered Solutions

Message:

HiFill FR® PC GF10 FR BK is a Polycarbonate (PC) product filled with 10% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Flame Retardant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.35	%	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	124		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	66.9	MPa	ASTM D638
Tensile Elongation (Break)	8.0	%	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	146	°C	
1.8 MPa, Unannealed	143	°C	
CLTE - Flow	3.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Dielectric Strength ¹	18	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	

Drying Time	4.0	hr
Rear Temperature	282 to 293	°C
Middle Temperature	282 to 293	°C
Front Temperature	282 to 293	°C
Processing (Melt) Temp	266 to 293	°C
Mold Temperature	82.2 to 121	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	30 to 60	rpm

NOTE

1.
- Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT