

Sindustris PC SG5010FA

Polycarbonate + ABS + Acrylic

Sincerity Australia Pty Ltd.

Message:

Sindustris PC SG5010FA is a Polycarbonate + ABS + Acrylic (PMMA) (PC+ABS+Acrylic) material. It is available in Asia Pacific for injection molding. Important attributes of Sindustris PC SG5010FA are:

Flame Rated
Flame Retardant
Halogen Free
High Gloss
Scratch Resistant

Typical applications include:
Electrical/Electronic Applications
Housings

General Information			
Features	Flame Retardant		
	Halogen Free		
	High Gloss		
	Scratch Resistant		
Uses	Computer Components		
	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	67.7	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	50	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2790	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	83	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.40 mm)	95.0	°C	ASTM D648
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746

RTI Str	80.0	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating		UL 94	
1.20 mm	V-0		
3.00 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 80.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	230 to 270	°C	
Middle Temperature	235 to 270	°C	
Front Temperature	235 to 270	°C	
Nozzle Temperature	235 to 270	°C	
Processing (Melt) Temp	245 to 270	°C	
Mold Temperature	90.0 to 120	°C	
Back Pressure	0.200 to 0.600	MPa	
Screw Speed	40 to 70	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	10 mm/min		
4.	10 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

