

LNP™ VERTON™ PX00700 compound

Polyamide 6

SABIC Innovative Plastics

Message:

LNP VERTON* PX00700 is a compound based on Nylon 6 resin containing proprietary fillers. Added feature of this grade is: Structural.

Also known as: LNP* VERTON* Compound PDX-P-00700

Product reorder name: PX00700

General Information			
Filler / Reinforcement	Proprietary		
Uses	Structural Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9510	MPa	ISO 527-2/1
Tensile Stress (Break)	188	MPa	ISO 527-2
Tensile Strain (Break)	2.7	%	ISO 527-2
Flexural Modulus	8210	MPa	ISO 178
Flexural Stress	249	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ¹ (23°C)	32	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ² (23°C)	74	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³			
0.45 MPa, Unannealed, 64.0 mm Span	214	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 64.0 mm Span	210	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	266 to 277	°C	
Front Temperature	277 to 288	°C	
Processing (Melt) Temp	266 to 277	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	80*10*4		
2.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

