

VAMPORAN 0024 V0 13

Polyphenylene Ether + PS

Vamp Tech

Message:

UL 94 V0, halogen free, good mechanical properties.

General Information			
Features	Halogen Free		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Water Absorption (Saturation)	0.070	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ASTM D638
Tensile Strength (Yield)	50.0	MPa	ASTM D638
Tensile Elongation (Break)	9.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	6.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	45	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	115	°C	ASTM D648A
Vicat Softening Temperature	130	°C	ASTM D1525 ¹
RTI Elec	100	°C	UL 746
RTI Imp	100	°C	UL 746
RTI Str	100	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating		UL 94	
1.60 mm	V-1		
3.20 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	290	°C	
Mold Temperature	90.0	°C	
NOTE			

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

