

Plaslube® TPX-PA6-95002

Polyamide 6
Techmer Engineered Solutions

Message:

Plaslube® TPX-PA6-95002 is a Polyamide 6 (Nylon 6) product. It can be processed by injection molding and is available in North America. Primary characteristic: lubricated.

General Information			
Additive	Lubricant		
Features	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.9	%	ASTM D955
Water Absorption (24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	78		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	47.6	MPa	ASTM D638
Tensile Elongation (Yield)	19	%	ASTM D638
Flexural Modulus	2140	MPa	ASTM D790
Flexural Strength	76.5	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.16		
vs. Steel - Static	0.12		
Wear Factor	100	10 ⁻⁸ mm ³ /N · m	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1000	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	143	°C	
1.8 MPa, Unannealed	71.1	°C	
CLTE - Flow	9.7E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength ¹	16	kV/mm	ASTM D149
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

