

NORYL™ PPX630 resin

Polyphenylene Ether + PS + PP

SABIC Innovative Plastics

Message:

30% GR PPE+PP. High elongation. high stiffness.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Rigidity, high		
	Extended tensile rate		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	2.6	g/10 min	ASTM D1238
Molding Shrinkage			Internal method
Flow: 3.20mm	0.20 - 0.23	%	Internal method
Transverse flow: 3.20mm	0.25 - 0.76	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	79.3	MPa	ASTM D638
Fracture	79.3	MPa	ASTM D638
Tensile Elongation ² (Break)	7.7	%	ASTM D638
Flexural Modulus ³ (50.0 mm Span)	5560	MPa	ASTM D790
Flexural Strength ⁴ (Break, 50.0 mm Span)	130	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	100	J/m	ASTM D256
23°C	170	J/m	ASTM D256
Unnotched Izod Impact (23°C)	830	J/m	ASTM D4812
Instrumented Dart Impact			ASTM D3763
-30°C, Total Energy	20.4	J	ASTM D3763
23°C, Total Energy	19.1	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.20mm	155	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	134	°C	ASTM D648
Vicat Softening Temperature	162	°C	ASTM D1525 ⁵
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	1.4E-5	cm/cm/°C	ASTM E831

Lateral: -40 to 40°C	7.7E-5	cm/cm/°C	ASTM E831
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	66 - 77	°C	
Drying Time	2.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	30 - 70	%	
Rear Temperature	243 - 288	°C	
Middle Temperature	249 - 288	°C	
Front Temperature	254 - 293	°C	
Nozzle Temperature	260 - 299	°C	
Processing (Melt) Temp	260 - 299	°C	
Mold Temperature	38 - 66	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	20 - 100	rpm	
Vent Depth	0.051 - 0.076	mm	
NOTE			
1.	Type 1, 5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		
5.	标准 B (120°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

