

KumhoSunny PBT/ABS HAB8720FR

Acrylonitrile Butadiene Styrene + PBT

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HAB8720FR is high flow, middle heat resistance PBT/ABS resin. HAB8720FR has high abrasion resistance and high flame retardant. HAB8720FR is mainly used in automobile parts, copier machine, printer housing, electric & electron parts,etc.

General Information			
Features	Flame Retardant		
	Good Abrasion Resistance		
	High Flow		
	Medium Heat Resistance		
Uses	Automotive Applications		
	Electrical Parts		
	Electrical/Electronic Applications		
	Housings		
	Printer		
UL File Number	E254819		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	35	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	35.0	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Modulus	1600	MPa	ASTM D790
Flexural Strength	550	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	180	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	88.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94

Injection	Nominal Value	Unit
Drying Temperature	90.0 to 100	°C
Drying Time	3.0 to 5.0	hr
Processing (Melt) Temp	220 to 250	°C
Mold Temperature	50.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

