

Star L PA6 30V D31

Polyamide 6
Eurostar Engineering Plastics

Message:

Star L PA6 30V D31 is a Molybdenum Disulfide Lubricated, Glass Fiber Reinforced, Polyamide 6 Injection Molding Resin

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Molybdenum Disulfide Lubricant		
Features	Lubricated		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Molding Shrinkage - Flow (4.00 mm)	0.20 to 0.40	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	170	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	8600	MPa	ISO 178
Flexural Stress	240	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ¹ (23°C)	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ² (23°C)	65	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed, 64.0 mm Span)	197	°C	ISO 75-2/Af
Melting Temperature (DSC)	225	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	240 to 250	°C	
Middle Temperature	250 to 260	°C	
Front Temperature	250 to 270	°C	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	50.0 to 90.0	°C	
NOTE			
1.	80*10*4		
2.	80*10*4		
3.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

