

BorLite™ OPE795

Linear Low Density Polyethylene

Borealis AG

Message:

BorLite OPE795 is a high molecular weight linear low density polyethylene film grade providing high melt strength for good processing behaviour of primary films on blown film technology as well as excellent draw down on mono directional orientation (MDO) lines. MDO-films made of this product are characterised by very high toughness and balanced MD/TD tear resistance.

BorLite OPE795 has been developed especially for property-enhancement of blown films through mono-directional orientation (MDO technology).

BorLite OPE795 is recommended for:

Heavy-duty bags

Industrial films

Consumer packaging

Compression packaging

Twist wrap

Label film

BorLite OPE795 contains antioxidant.

General Information			
Additive	Antioxidation		
Features	Ultra high toughness		
	High molecular weight		
	Antioxidation		
	Workability, good		
	Good stripping		
	Good melt strength		
Uses	Good tear strength		
	Packaging		
	Films		
	Label		
	Directional film		
	Heavy packing bag		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.931	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	0.20	g/10 min	ISO 1133
190°C/21.6 kg	20	g/10 min	ISO 1133
190°C/5.0 kg	0.85	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
Tensile Modulus			ISO 527-3
MD: 25 µm, blown film	950	MPa	ISO 527-3

TD: 25 µm, blown film	950	MPa	ISO 527-3
Tensile Stress			ISO 527-3
MD: Yield, 25 µm, blown film	180	MPa	ISO 527-3
TD: Yield, 25 µm, blown film	20.0	MPa	ISO 527-3
MD: 25 µm, blown film	190	MPa	ISO 527-3
TD: 25 µm, blown film	21.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 25 µm, blown film	25	%	ISO 527-3
TD: Broken, 25 µm, blown film	750	%	ISO 527-3
Dart Drop Impact (25 µm)	820	g	ISO 7765-1
Elmendorf Tear Strength ¹			ISO 6383-2
MD : 25.0 µm	160.0	kN/m	ISO 6383-2
TD : 25.0 µm	300.0	kN/m	ISO 6383-2
Puncture Resistance - Energy to Break (25.0 µm) ²			ISO 7765-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	108	°C	ISO 306/A
Melting Temperature	127	°C	ISO 11357-3
Optical	Nominal Value	Unit	Test Method
Haze (25.0 µm, Blown Film)	14	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Film properties are measured on a 25 µm MD-oriented film sample, DDR 1:6. Primary film produced on a 70 mm extruder, BUR=1:2.7, Die gap: 1.2 mm, FLH 2-4 DD, thickness 150 µm			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	190	°C	
Cylinder Zone 2 Temp.	190	°C	
Cylinder Zone 3 Temp.	190	°C	
Cylinder Zone 4 Temp.	190	°C	
Cylinder Zone 5 Temp.	190	°C	
Melt Temperature	190 - 210	°C	
Die Temperature	190	°C	
NOTE			
1.	Blown Film		
2.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

