## Tectron E1188

# Thermoplastic Vulcanizate TECTRON Systems Pte Ltd

#### Message:

Thermoplastic vulcanizate with excellent oil, chemical and heat resistance. It can withstand temperatures ranging from 50°C to 130°C. Tectron E series are available in concentrate and compound with hardness ranging from 45A - 90A. The concentrate is designed for compounders to obtain olefenic TPVs with the addition of PP and other chemicals. It can also be used as an additive to improve the overall properties of your olefinic compounds.

| General Information          |                          |       |             |
|------------------------------|--------------------------|-------|-------------|
| Features                     | Good chemical resistance |       |             |
|                              | Heat resistance, high    |       |             |
|                              | Oil resistance           |       |             |
|                              |                          |       |             |
| Appearance                   | Yellow                   |       |             |
| Forms                        | Particle                 |       |             |
| Processing Method            | Injection molding        |       |             |
| Physical                     | Nominal Value            | Unit  | Test Method |
| Specific Gravity             | 0.900                    | g/cm³ | ASTM D792   |
| Hardness                     | Nominal Value            | Unit  | Test Method |
| Rockwell Hardness (A-Scale)  | 70                       |       | ASTM D785   |
| Elastomers                   | Nominal Value            | Unit  | Test Method |
| Tensile Stress (100% Strain) | 1.80                     | MPa   | ASTM D412   |
| Tensile Strength (Yield)     | 4.00                     | MPa   | ASTM D412   |
| Tensile Elongation (Break)   | 960                      | %     | ASTM D412   |
| Compression Set              |                          |       | ASTM D395   |
| 25°C, 22 hr                  | 35                       | %     | ASTM D395   |
| 100°C, 22 hr                 | 68                       | %     | ASTM D395   |
| Injection                    | Nominal Value            | Unit  |             |
| Drying Temperature           | 70.0                     | °C    |             |
| Drying Time                  | 2.0 - 4.0                | hr    |             |
| Rear Temperature             | 160 - 170                | °C    |             |
| Middle Temperature           | 180 - 190                | °C    |             |
| Front Temperature            | 180 - 200                | °C    |             |
| Nozzle Temperature           | 190 - 210                | °C    |             |
| Mold Temperature             | 30.0 - 40.0              | °C    |             |
| Back Pressure                | 0.00 - 0.0800            | МРа   |             |
| Screw Speed                  | 50 - 110                 | rpm   |             |
| Injection instructions       |                          |       |             |

 $Injection \ Speed: 20 \ to \ 80 \ mm/s1st \ Stage-Boost \ Pressure: 1350 \ to \ 6000 Hold \ Time \ (thick part): 2 \ to \ 15 \ sec$ 

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

