

CEFOR™ 1211P

Linear Low Density Polyethylene Resin

The Dow Chemical Company

Message:

CEFOR 1211P is a butene Linear Low Density Polyethylene for general blown film applications.

Main Characteristics:

Used in Industrial, Food & Specialty Packaging

Better optics and processability

Better color stability

Good sealing performance

Complies with:

U.S. FDA 21 177.1520 (c) 3.2a

EU. No 10/2011

Consult the regulations for complete details.

Additive:

Antiblock: No

Slip: No

Processing Aid: No

General Information			
Agency Ratings	FDA 21 CFR 177.1520(c) 3.2a Europe No 10/2011		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	51	µm	
Film Puncture Resistance (51 µm)	8.19	J/cm³	Internal method
secant modulus			ASTM D882
2% secant, MD: 51 µm	183	MPa	ASTM D882
2% secant, TD: 51 µm	217	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 51 µm	10.3	MPa	ASTM D882
TD: Yield, 51 µm	11.0	MPa	ASTM D882
MD: Fracture, 51 µm	31.7	MPa	ASTM D882
TD: Fracture, 51 µm	25.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture, 51 µm	660	%	ASTM D882
TD: Fracture, 51 µm	710	%	ASTM D882
Dart Drop Impact (51 µm)	100	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 51 µm	110	g	ASTM D1922

TD : 51 μm	260	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	101	°C	ASTM D1525
Melting Temperature (DSC)	116	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Gloss (20°, 50.8 μm)	69		ASTM D2457
Haze (50.8 μm)	11	%	ASTM D1003
Extrusion instructions			

Fabrication Conditions For Blown Film:

Melt Temperature: 440°F (227°C)

Die Gap: 70mil (1.8mm)

Output: 120 lb/hr (55 Kg/hr)

Blow Up Ratio: 2.5:1

Frost Line Height: 28 in. (71 cm)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

