

LNP™ THERMOCOMP™ DX10311 compound

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

DX10311 is 30% glass fiber reinforced, impact modified polycarbonate resin. High flow and good ductility.

General Information			
UL YellowCard	E207780-101133363		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Impact Modifier		
Features	Ductile		
	High Flow		
	Impact Modified		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Melt Volume-Flow Rate (MVR) (300°C/5.0 kg)	37.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Flow : 3.20 mm	0.10 to 0.30	%	
Across Flow : 3.20 mm	0.20 to 0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	8340	MPa	ASTM D638
--	8260	MPa	ISO 527-2/1
Tensile Strength			
Break ²	117	MPa	ASTM D638
Break	119	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	2.6	%	ASTM D638
Break	2.7	%	ISO 527-2/5
Flexural Modulus			
--	7670	MPa	ASTM D790
-- ⁴	7730	MPa	ISO 178
Flexural Strength			
--	190	MPa	ASTM D790
--	182	MPa	ISO 178
--	181	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength (23°C)	57	kJ/m ²	ISO 179/2U
Notched Izod Impact (23°C)	200	J/m	ASTM D256
Unnotched Izod Impact (23°C)	750	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm)	128	°C	ASTM D648
CLTE			ASTM E831
Flow : -40 to 40°C	1.9E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.4E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 110	°C	
Drying Time	3.0 to 5.0	hr	
Rear Temperature	250 to 280	°C	
Middle Temperature	280 to 320	°C	
Front Temperature	280 to 320	°C	
Nozzle Temperature	280 to 320	°C	
Processing (Melt) Temp	280 to 320	°C	
Mold Temperature	90.0 to 120	°C	
Back Pressure	1.00 to 5.00	MPa	
Screw Speed	30 to 100	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT