

POPELEN A-352

Polypropylene Impact Copolymer

Lotte Chemical Corporation

Message:

High Stiffness, Heat Resistance, High Impact Strength

General Information			
Features	Block Copolymer		
	High Heat Resistance		
	High Impact Resistance		
	High Stiffness		
Uses	Appliances		
	Automotive Applications		
	Electrical/Electronic Applications		
	Industrial Applications		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	94		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	32.4	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	2650	MPa	ASTM D790
Flexural Strength	39.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-10°C	29	J/m	
23°C	54	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	136	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

