

Stanyl® ForTii™ F81

Polyamide 4T
DSM Engineering Plastics

Message:

Stanyl® ForTii™ F81 is a Polyamide 4T (Nylon 4T) material filled with 15% glass fiber. It is available in Asia Pacific, Europe, or North America. Important attributes of Stanyl® ForTii™ F81 are:
Flame Rated
Flame Retardant
Halogen Free

General Information	
UL YellowCard	E47960-100713842
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight
Additive	Flame Retardant
Features	Flame Retardant
	Good Flow
	Halogen Free
	Low (to None) Phosphorus Content

Physical	Dry	Conditioned	Unit	Test Method
Density	1.34	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.2	--	%	
Flow	0.50	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	2.2	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	7000	7000	MPa	ISO 527-2
Tensile Stress (Break)	105	110	MPa	ISO 527-2
Tensile Strain (Break)	2.0	2.1	%	ISO 527-2
Flexural Modulus	7000	7000	MPa	ISO 178
Flexural Stress	180	175	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	30	30	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	300	--	°C	ISO 75-2/A
Melting Temperature ¹	325	--	°C	ISO 11357-3
CLTE				ASTM D696

Flow	4.0E-5	--	cm/cm/°C	
Transverse	5.5E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength	33	--	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.750 mm)	V-0	--		IEC 60695-11-10, -20
Injection	Dry	Unit		
Drying Temperature	100		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	320 to 330		°C	
Middle Temperature	325 to 335		°C	
Front Temperature	330 to 335		°C	
Nozzle Temperature	330 to 335		°C	
Processing (Melt) Temp	330 to 340		°C	
Mold Temperature	100 to 150		°C	
Injection Rate	Moderate-Fast			
Back Pressure	0.500 to 3.00		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

