

THERMOLAST® K TC8FRZ (Series: FR)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The FR Series is your material solution for applications requiring high flame retardance. The compounds are halogen free and available in natural and black colors.

Typical applications

Cable holders

Seals for in-wall outlets

Seals for plugs

Seals for switch boxes

Material advantages

Easy coloring (compounds in natural colors)

Excellent mechanical properties

Halogen free (reduction of toxic fire gases)

Self-extinguishing, no dripping of flaming particles

UL 94-V0 (3mm) listed

General Information			
UL YellowCard	E214822-591064		
Features	Flame Retardant		
	Halogen Free		
	Self Extinguishing		
Uses	Seals		
Appearance	Black		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	79		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Yield)	5.00	MPa	ISO 37
Tensile Elongation ² (Break)	600	%	ISO 37
Tear Strength ³	24	kN/m	ISO 34-1
Compression Set ⁴			ISO 815
23°C, 72 hr	25	%	
70°C, 24 hr	45	%	
100°C, 24 hr	84	%	
Flammability	Nominal Value		Test Method
Flame Rating (3.00 mm)	V-0		UL 94
Extrusion	Nominal Value	Unit	

Drying Temperature	80.0	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Cylinder Zone 1 Temp.	160	°C
Cylinder Zone 2 Temp.	190	°C
Cylinder Zone 3 Temp.	220	°C
Die Temperature	180 to 190	°C

NOTE

- | | |
|----|---------------------------|
| 1. | Type S2, 200 mm/min |
| 2. | Type S2, 200 mm/min |
| 3. | Method Bb, Angle (Nicked) |
| 4. | Method A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

