

RAMLLOY PBB702

Polycarbonate + ABS
Polyram Ram-On Industries

Message:
UV STABILIZED PC/ABS ALLOY FOR INJECTION MOULDING APPLICATIONS.

General Information			
Additive	UV Stabilizer		
Features	Good UV Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
240°C/5.0 kg	7.0	g/10 min	ASTM D1238
300°C/1.2 kg	7.0	g/10 min	ISO 1133
Molding Shrinkage			
Flow	0.40 to 0.70	%	
--	0.40 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1800	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	50.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	40	%	ASTM D638, ISO 527-2
Flexural Modulus	2100	MPa	ASTM D790, ISO 178
Flexural Strength	80.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	500	J/m	ASTM D256
23°C	40	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	120	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	100	°C	ASTM D648, ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	4.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	

Rear Temperature	230 to 240	°C
Middle Temperature	240 to 250	°C
Front Temperature	250 to 265	°C
Mold Temperature	50.0 to 90.0	°C
Injection Pressure	70.0 to 100	MPa
Holding Pressure	35.0 to 70.0	MPa
Back Pressure	0.350 to 0.700	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

