

Zytel® HTN 51G15HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN

DuPont Performance Polymers

Message:

15% Glass Reinforced, PPA, High Performance Polyamide

General Information				
UL YellowCard		E41938-234557		
Filler / Reinforcement		Glass Fiber, 15% Filler by Weight		
Additive		Heat Stabilizer		
		Lubricant		
		Mold Release		
Features		Heat Stabilized		
		Lubricated		
Agency Ratings		UL Unspecified Rating		
Forms		Pellets		
Processing Method		Injection Molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
Part Marking Code (ISO 11469)		>PA6T/XT-GF15<		
Part Marking Code (SAE J1344)		>PPA-GF15<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.30	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.0	--	%	
Flow	0.40	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	6500	--	MPa	ISO 527-2
Tensile Stress (Break)	120	--	MPa	ISO 527-2
Tensile Strain (Break)	2.1	--	%	ISO 527-2
Flexural Modulus	5700	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0	--	kJ/m ²	
23°C	6.0	--	kJ/m ²	
Charpy Unnotched Impact Strength (23°C)				ISO 179/1eU
25		--	kJ/m ²	

Notched Izod Impact Strength				ISO 180/1A
-40°C	6.0	--	kJ/m ²	
23°C	6.0	--	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	276	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	254	--	°C	ISO 75-2/A
Melting Temperature ¹	300	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	3.0E-5	--	cm/cm/°C	
Flow : -40 to 23°C	5.7E-5	--	cm/cm/°C	
Transverse	6.4E-5	--	cm/cm/°C	
Transverse : -40 to 23°C	3.0E-5	--	cm/cm/°C	
Transverse : 55 to 160°C	7.7E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	--	ohms·cm	IEC 60093
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.750 mm	HB	--		
1.50 mm	HB	--		
Oxygen Index	23	--	%	ISO 4589-2
NOTE				

1. First Heat

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT