

LNP™ STAT-KON™ RFD02 compound

Polyamide 66

SABIC Innovative Plastics Asia Pacific

Message:

LNP STAT-KON RFD02 is a compound based on Nylon 66 resin containing Glass Fiber, Carbon Powder. Added features of this material include: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound RF

Product reorder name: RFD02

General Information			
Filler / Reinforcement	Glass\Carbon Powder		
Features	Electrically Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	1.0 to 1.2	%	ASTM D955
Across Flow : 24 hr	1.4 to 1.6	%	ASTM D955
Across Flow : 24 hr	1.5	%	ISO 294-4
Flow : 24 hr	1.1	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.50	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	8270	MPa	ASTM D638
--	7400	MPa	ISO 527-2/1
Tensile Strength			
Break	77.9	MPa	ASTM D638
Break	74.0	MPa	ISO 527-2
Tensile Elongation			
Break	5.5	%	ASTM D638
Break	5.2	%	ISO 527-2
Flexural Modulus			
--	5520	MPa	ASTM D790
--	6300	MPa	ISO 178
Flexural Strength			
--	131	MPa	ASTM D790
--	139	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	37	J/m	ASTM D256
23°C ²	3.2	kJ/m ²	ISO 180/1A

Unnotched Izod Impact			
23°C	210	J/m	ASTM D4812
23°C ³	14	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	252	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	256	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	237	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	239	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	6.8E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	6.9E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	4.7E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	4.8E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+5	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	282 to 304	°C	
Mold Temperature	93.3 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

