# Premier LS00715 - D

## Linear Low Density Polyethylene

#### Premier Polymers, LLC.

#### Message:

Premier LS00715 is a high strength linear low density polyethylene resin suitable for applications requiring high strength, tear resistance, clarity, and processability. Meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

General Information			
Additive	High Antiblock		
	High Slip		
Features	Food Contact Acceptable		
	Good Processability		
	Good Tear Strength		
	High Antiblocking		
	High Clarity		
	High Slip		
	High Strength		
	Low Density		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Density	0.915	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	0.70	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD : Yield	10.3	MPa	
TD : Yield	10.3	MPa	
MD : Break	39.3	MPa	
TD : Break	34.5	MPa	
Tensile Elongation			ASTM D882
MD : Break	700	%	
TD : Break	900	%	
Dart Drop Impact	530	g	ASTM D1709A
Elmendorf Tear Strength			ACTNA D1000
Linendon real Strength			ASTM D1922
MD	470	g	ASTM D1922

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

