

RTP 152 HI

Polypropylene Copolymer
RTP Company

Message:
Copolymer - Flame Retardant

General Information			
Features	Copolymer		
	Flame Retardant		
RoHS Compliance		Contact Manufacturer	
Processing Method		Injection Molding	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0 to 5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.5 to 2.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.010	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	965	MPa	ASTM D638
Tensile Strength	19.3	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Flexural Modulus	827	MPa	ASTM D790
Flexural Strength	22.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	640	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	No Break		ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	43.3	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm, ** Values per RTP Company testing.)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	32.2 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

