

Braskem PE HDI0861U1

High Density Polyethylene

Braskem IDESA

Message:

HDI0861U1 is a high density polyethylene copolymer with a narrow molecular weight distribution. Parts fabricated from this material exhibit a glossy surface finish, and have good impact strength and rigidity. This material meets the Food and Drug Administration requirements of 21CFR 177.1520.

Applications:
Specifically for boxes, trays, industrial totes, plastic containers, buckets.

Process:
Injection Molding.

General Information			
Features	Good Rigidity		
	Copolymer		
	Impact resistance, good		
	Excellent appearance		
	Narrow molecular weight distribution		
Uses	Industrial application		
	Container		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.961	g/cm ³	ASTM D4883
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance	5.00	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	32.4	MPa	ASTM D638
Tensile Elongation (Break)	> 800	%	ASTM D638
Flexural Modulus - Tangent	1.66	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	87.0	°C	ASTM D648
Brittleness Temperature	< -75.0	°C	ASTM D746
Vicat Softening Temperature	128	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

