

Rotuba CAB B902 (11% Plasticizer)

Cellulose Acetate Butyrate

Rotuba Extruders, Inc.

Message:

Rotuba CAB B902 (11% Plasticizer) is a cellulose acetate butyrate (CAB) product. It can be processed by injection molding and is available in North America. Rotuba CAB B902 (Plasticizer 11%) has applications including optics/lenses, automotive industry, commercial/office supplies, consumer goods and handles.

Features include:

environmental protection/green

Good dimensional stability

Impact resistance

good weather resistance

| General Information | | | |
|----------------------------|-----------------------------------|-------------------|-------------|
| Features | Good dimensional stability | | |
| | Updatable resources | | |
| | Low temperature impact resistance | | |
| | Good weather resistance | | |
| | amorphous | | |
| Uses | Handle | | |
| | Optical applications | | |
| | Application in Automobile Field | | |
| | Toys | | |
| | Stationery | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.19 | g/cm ³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.20 - 0.60 | % | ASTM D955 |
| Water Absorption (24 hr) | 1.4 | % | ASTM D570 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D638 |
| Yield | 27.6 | MPa | ASTM D638 |
| Fracture | 35.9 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 30 | % | ASTM D638 |
| Flexural Modulus | 1100 | MPa | ASTM D790 |
| Flexural Strength | 35.9 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 260 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |

| | | | |
|---|---------------|------|------------|
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 73.3 | °C | ASTM D648 |
| Vicat Softening Temperature | 103 | °C | ASTM D1525 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 229 | °C | |
| Mold Temperature | 57 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

