

# InnoTuf® TP-4055

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

TP-4055 is an impact resistant polyurethane formulated for hand-batch processing, vacuum assist casting or meter mix dispense methods. Excellent physical properties can be obtained with a mild post cure without the utilization of mercury, MOCA, or TDI. TP-4055 is a tough polyethylene/polypropylene simulated product with a very low mixed viscosity.

General Information			
Features	Good Toughness		
	High Impact Resistance		
	Low Viscosity		
RoHS Compliance	RoHS Compliant		
Appearance	Translucent		
Processing Method	Vacuum Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Hardener	1.07	g/cm³	
Cured	1.08	g/cm³	
Base Resin	1.21	g/cm³	
Molding Shrinkage - Flow	0.10 to 0.50	%	ASTM D2566
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	724	MPa	ASTM D790
Flexural Strength	26.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	91	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	64.0	°C	ASTM D648
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 100		
Hardener	Mix Ratio by Weight: 100		
	Mix Ratio by Weight: 76		
Resin	Mix Ratio by Volume: 67		

Demold Time	120 to 240	min	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
38°C <sup>1</sup>	0.075	Pa·s	
38°C <sup>2</sup>	0.50	Pa·s	
38°C <sup>3</sup>	1.6	Pa·s	
Curing Time <sup>4</sup>	26	hr	
Gel Time	6.0 to 10	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	65 to 75		ASTM D2240
Tensile Strength	31.8	MPa	ASTM D638
Tensile Elongation at Break	35	%	ASTM D638
NOTE			
1.	Resin		
2.	Mixed		
3.	Hardener		
4.	2 hours at 150°F + 24 hours at 77°F		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT