

Wanthane® WHT-8885

Thermoplastic Polyurethane Elastomer (Polyether)

Wanhua Chemical Group Co., Ltd.

Message:

TYPE: Polyether-based grade Extrusion grade
FEATURES: Excellent hydrolytic stability, fungus resistance, good processability, good low-temperature flexibility
APPLICATIONS: Hose jacketing, fabric coating, etc.

General Information			
Features	Flexibility at low temperatures		
	Antibacterial property		
	Workability, good		
	Hydrolysis stability		
Uses	Jacketing		
	Fabric coating		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
DIN Abrasion	40.0	mm ³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	8.00	MPa	ASTM D412
300% strain	17.0	MPa	ASTM D412
Tensile Strength (Break)	45.0	MPa	ASTM D412
Tensile Elongation (Break)	460	%	ASTM D412
Tear Strength	121	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	90 - 100	°C	
Drying Time	2.0 - 3.0	hr	
Suggested Max Moisture	0.030	%	
Screw L/D Ratio	25.0:1.0 to 30.0:1.0		
Screw Compression Ratio	2.0 : 1.0 - 3.0 : 1.0		
Extrusion	Nominal Value	Unit	

Drying Temperature	90 - 100	°C
Drying Time	2.0 - 3.0	hr
Suggested Max Moisture	0.030	%
Cylinder Zone 1 Temp.	170	°C
Cylinder Zone 2 Temp.	175	°C
Cylinder Zone 3 Temp.	180	°C
Cylinder Zone 4 Temp.	185	°C
Adapter Temperature	190	°C
Die Temperature	185	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

