

Stanyl® TS272A1

Polyamide 46

DSM Engineering Plastics

Message:

Stanyl® TS272A1 is a Polyamide 46 (Nylon 46) material filled with aramid fiber. It is available in Asia Pacific or North America. Primary attribute of Stanyl® TS272A1: Wear Resistant.

General Information			
Filler / Reinforcement	Aramid Fiber		
Features	Good Wear Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	2.2	%	
Flow	2.2	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	3.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ISO 527-2
Tensile Stress (Break)	80.0	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Flexural Modulus	2400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	160	°C	ISO 75-2/A
Melting Temperature ¹	295	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0 to 8.0	hr	
Rear Temperature	280 to 320	°C	
Middle Temperature	300 to 320	°C	
Front Temperature	300 to 320	°C	
Nozzle Temperature	300 to 320	°C	
Processing (Melt) Temp	305 to 320	°C	
Mold Temperature	80.0 to 120	°C	
Injection Rate	Moderate-Fast		
Back Pressure	2.00 to 10.0	MPa	
Screw Compression Ratio	2.5:1.0		

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

