# Vipel® F701-FBN-15

### Polyester Alloy

AOC, L.L.C.

#### Message:

AOC's Vipel F701 Series resins are high molecular weight, two-stage isophthalic, unsaturated polyester resin with the wet out, cure and handling characteristics of general purpose resins.

They have an excellent shelf life and are ideal for filament winding and spray-up. A few selected resins are listed below including the high viscosity base resin, Vipel F701-FHG-00.

BENEFITS

Corrosion resistance

AOC's Vipel F701 series resins provide excellent corrosion resistance when used in contact with inorganic and organic acids. Solvent resistance is field-proven for many petroleum products such as kerosene, heating oil and crude oils.

Refer to AOC's "Corrosion Resistant Resin Guide" for corrosion resistance information or for questions regarding suitability of a resin to any particular chemical environment contact AOC.

Versatile

Suitable for various fabricating methods such as hand lay-up, spray-up and filament winding.

General Information					
Features	High molecular weight				
	m-benzene dimethyl				
	Solvent resistance				
	Good corrosion resistance				
	acid resistance				
	Oil resistance				
Agency Ratings	FDA 21 CFR 177.2420				
Forms	Liquid				
Processing Method	Filament power winding				
	Sprayable				
	Hand coating				
Physical	Nominal Value	Unit	Test Method		
Styrene Content	48	%			
Gel to Peak	10.0	min			
Peak Exotherm	199	°C			
Thixotropic Index <sup>1</sup>	2.50				
Hardness	Nominal Value	Unit	Test Method		
Barcol Hardness	43		ASTM D2583		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus	3790	MPa	ASTM D638		
Tensile Strength	83.4	MPa	ASTM D638		
Tensile Elongation (Break)	2.8	%	ASTM D638		
Flexural Modulus	4210	MPa	ASTM D790		
Flexural Strength	127	MPa	ASTM D790		

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	107	°C	ASTM D648
Uncured Properties	Nominal Value	Unit	
Density	1.06	g/cm³	
Viscosity (Brookfield LV)	0.55	Pa·s	
Gel Time (25°C)	15	min	
NOTE			
1.	2/20 rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

