

Iupilon® EGN2010DR 9911A

Polycarbonate

Mitsubishi Engineering-Plastics Corp

Message:

Iupilon® EGN2010DR 9911A is a Polycarbonate (PC) material filled with 10% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of Iupilon® EGN2010DR 9911A are:

Flame Rated

Flame Retardant

Good Aesthetics

Halogen Free

General Information			
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Additive	Flame Retardant		
Features	Bromine Free		
	Flame Retardant		
	Good Surface Finish		
	Low (to None) Phosphorus Content		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Molding Shrinkage			
Across Flow : 3.20 mm	0.30 to 0.50	%	
Flow : 3.20 mm	0.30 to 0.50	%	
Water Absorption (Saturation, 23°C)	0.14	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	62.0	MPa	ISO 527-2
Tensile Strain (Break)	5.6	%	ISO 527-2
Flexural Modulus	3100	MPa	ISO 178
Flexural Stress	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	70	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	138	°C	ISO 75-2/B
1.8 MPa, Unannealed	133	°C	ISO 75-2/A
Electrical	Nominal Value		Test Method
Comparative Tracking Index (CTI)	PLC 3		UL 746

Flammability	Nominal Value	Test Method
Flame Rating		UL 94
0.750 mm	V-2	
1.50 mm	V-0	
Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	4.0 to 8.0	hr
Rear Temperature	270 to 290	°C
Middle Temperature	280 to 300	°C
Front Temperature	280 to 300	°C
Nozzle Temperature	280 to 300	°C
Mold Temperature	80.0 to 120	°C
Injection Pressure	50.0 to 150	MPa
Screw Speed	50 to 100	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

